



Class: EN ISO 20345:2011 S1P SRC Sizes: 35-47 Instep: 12 Weight(±10%): 475 gr. (*)

TECHNICAL SHEET ART. FRISBEE

Description Low shoe in black MESH with padded storm-cuff, 100% polyester lining, Non-Metallic HRP Insole, SPORT-LITE Insole anatomic antistatic and antibacterical, monodensity polyurethane sole, bending resistant, abrasion resistant, oil resistant, slip resistant, ESD.

Suggested sectors of usage Servicing , Mechanical Industry, Professional / Craftsman , Electronic & Electrotechnic, Logistic/Packaging

Care and Maintenance clean periodically the outsole and the upper with non aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source.



Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirements
Toe Cap : Non-Metallic Thin Cap toe cap, impact resistant 200 J and compression resistant 15kN	5.3.2.3	Impact resistance	mm	14,5	≥14
	5.3.2.4	Compression resistance	mm	16,0	≥ 14
Midsole: non metallic HRP Insole with high tenacity fibres layers, ceramized and treated with plasma	6.2.1.1	Perforation resistance	N	1.100 without holes	≥ 1.100
ESD footwear : dissipation capacity of the electrostatic charge	EN ISO	Resistance to floor			
	613 4 0	(footwear/floor resistance)	Ohm	4,16 x 10 ⁷	$<$ 1,00 x 10 8 Ω
	5-1:2016	Transverse resistance of the sole	Ohm	4,65 x 10 ⁷	\leq 1,00 x $10^8 \Omega$
		Chargeability	V	<20 V	< 100 V
Capacity of Energy Absorption in the heel area	6.2.4	Energy absorption in the heel area	J	22,0	≥ 20
Upper: Black MESH	5.4.6	Water vapour permeability	mg/cm ² h	9,3	≥ 0,8
		Coefficient of permeability	mg/cm ²	74,5	≥ 15
	5.4.3	Tearing Strength	N	135	≥ 60
Vamp and Quarter Lining : honeycomb finished polyester, breathable, abrasion	5.5.3	Water vapour permeability	mg/cm ² h	6,8	≥ 2
resistant, black colour		Coefficient of permeability	mg/cm ²	54,4	≥ 20
	5.5.1	Tearing Strength	N	25	≥ 15
	5.5.2	Abrasion resistance (dry)	cycles	no rupture	25.600
		Abrasion resistance (wet)	cycles	no rupture	12.800
Quarter Lining : honeycomb finished polyester, breathable, abrasion resistant, green fluo colour	5.5.3	Water vapour permeability	mg/cm ² h	6,1	≥ 2
		Coefficient of permeability	mg/cm ²	54,0	≥ 20
	5.5.1	Tearing Strength	N	25	≥ 15
	5.5.2	Abrasion resistance (dry)	cycles	no rupture	25.600
		Abrasion resistance (wet)	cycles	no rupture	12.800
Insole lining: textile anti perforation midsole HRP insole	5.7.3	Water Absorption	mg/cm ²	76	≥ 70
		Ability to release water		99%	≥ 80%
Sole : mono-density polyurethane , bending resistant, abrasion resistant, oil	5.8.2	Tearing Strength	kN/m	6,4	≥ 5
resistant, slip resistant, ESD	5.8.3	Abrasion resistance	mm³	147	≤ 250
	5.8.4	Bending resistance	mm	1	≤ 4
	5.8.5	Hydrolysis	mm	2	≤ 6
	6.4.2	Hydrocarbons resistance (volume increase)	%	1 %	≤ 12%
	5.11	Slip resistance on ceramic floor with water and	flat	0,45	≥ 0,32
		detergent	inclined	0,34	≥ 0,28
		Slip resistance on steel floor with glycerine	flat	0,22	≥ 0,18
			inclined	0,18	≥ 0,13